

# Water Absorption of Hardened Concrete Treated with Water Repellant Coating

ASTM D6489

Test Lab : American Engineering Testing

Test Report : P0042463

Product Tested : Dynaseal DS-300

Substrate : Concrete Block , Treated with 1 coat of DS-300

Immersion Period : 48 hours

Block has surface moisture blotted off and quickly weighed

Result : 1.48% weight gain